NoMorePly®
BoardingSystems

Built for **Performance**
***Trusted** in Every Layer*

A: **No**More**Ply** Boarding Systems / 5 Hawthorn Park / Seacroft / LS14 1PQ
E: Sales@**No**More**Ply**.co.uk **T:** 0113 202 2010 **W:** www.**No**More**Ply**.co.uk

Technical Data

TG4 **22mm Fibre** Cement **Board 1200 x 600mm**

NoMore**Ply** 22mm TG4 Fibre Cement Board is manufactured to improve strength and durability for direct to joist applications, internally and externally. It meets the performance requirements of BS EN 12467:2012 for Fibre Cement Flat Sheets.

Specification	
Board Weight	24.8kg
Tolerance	+/- 5%
Test Standard	BS EN 12467:2016 + A1:2016
Performance	
Density	1.28g cm^3
U Value	0.1279 W/m^2K
Water Impermeability (unprimed)	No water formation after 24 hours Damp patch covers tested area
Water Impermeability (primed)	No water formation after 24 hours No damp patch in tested area after 192 hours
Reaction to Fire Test Standard	Euro Class A1 Non-Combustible (A1fl) EN ISO 1182 & EN ISO 1716
Mechanical Characteristics - Bending Strength (MOR)	8.067 MPa (N/mm^2)
Compression Strength	34 MPa
Thermal Conductivity	0.27907 W/mK
Thermal Resistance	0.07883 m^2K/W
Volatile Organic Compound (VOC) Test Test Standard	Result: Not Detected ISO 10580

All information within this document is copyright of **No**More**Ply** Boarding Systems